

Asahi

#500

T/C bias tape


T/C バイアステープ

T/C bias tape

T/C バイアステープ

[#500]

Quality Sample



※ Will be discontinued due to limited stock.
 ※ 在庫限りで販売終了となります

Color Samples



Polyester 65%
Cotton 35%
ポリエステル 65%
綿 35%

Fabric width 120cm
生地巾 120cm



Washing cautions 洗濯上の注意

- Wash well with water. Hang out to dry immediately.
- Do not leave wrung or soaked in water for a long time.
- Do not use detergents with bleaching agents as they may cause the material to discolor. A neutral detergent is most suitable.
- 水洗いは充分にしてください。水洗いのあとは早く干してください。
- 絞ったままや水につけたままでの長時間にわたる放置はさけてください。
- 漂白剤入りの洗剤をご使用になりますと変色することがありますので、ご使用にならないでください。中性洗剤が最適です。

Ironing cautions アイロンがけの注意

- Dry completely before ironing. Ironing partially dry material may cause the color to fade.
- なま乾きのままでアイロンをかけると、色落ちすることがありますのでよく乾かしてからアイロンをかけてください。

Care symbols 取扱い絵表示



Color list カラー一覧						Colorfastness 染色堅牢度	
501	V17	V105				Light 耐光堅牢度	Class 3 3級
503	V18	V109					
507	V19	V112					
509	V36	V113					
517	V37	V114					
518	V44					Dry rubbing 乾摩擦堅牢度	Class 4~5 4~5級
522	V46						
527	V50						
534	V101					Wet rubbing 湿摩擦堅牢度	Class 4 4級
551	V102						
561	V103					Water 水堅牢度	Class 4~5 4~5級
502	542	V13	V45	V108	V123	Light 耐光堅牢度	Class 3~4 3~4級
504	543	V14	V52	V110	V124		
508	544	V16	V54	V111		Dry rubbing 乾摩擦堅牢度	Class 4 4級
510	548	V22	V60	V115			
513	554	V23	V64	V116			
519	558	V28	V65	V117			
532	559	V30	V70	V118			
535	V1	V33	V76	V119		Wet rubbing 湿摩擦堅牢度	Class 3 3級
536	V5	V40	V104	V120			
538	V8	V41	V106	V121		Water 水堅牢度	Class 4 4級
540	V12	V42	V107	V122			
505	530	V11	V53	V71		Light 耐光堅牢度	Class 4 4級
506	531	V21	V55	V72			
515	545	V24	V56	V73		Dry rubbing 乾摩擦堅牢度	Class 3 3級
516	553	V25	V57	V74			
521	555	V26	V58	V75			
523	560	V31	V59	V77			
524	V2	V34	V61	V78			
525	V3	V35	V62			Wet rubbing 湿摩擦堅牢度	Class 3 3級
526	V4	V38	V66				
528	V9	V43	V67			Water 水堅牢度	Class 3~4 3~4級
529	V10	V51	V68				